

# TEST REPORT

**149453 / 1**

Date received: 12/11/12

Date of test: 10/12/12

Date of issue: 20/12/12

Sample name: Fior di fiemme

D.K.Z. S.R.L.  
VIA DELL'ARTIGIANATO 8  
38037 PREDAZZO (TN)  
ITALIA

## Formaldehyde emission, 1 m3 chamber method EN 717-1:2004

Sampling by:

Customer

Test start:

10/12/12

Test end:

17/12/12

Test conditions:

23±0,5°C and 45±3% R.H.

Analytical procedure:

See #9 - 2 sampling/day

Sample description:

Type of board:

Parquet

Thickness:

15,0 mm

Total surface:

1,0 m2

Test results:

| Steady state at ___ hours | mg/m3 | ppm  |
|---------------------------|-------|------|
| at 23°C                   | 0,01  | 0,01 |

Note: the conformity of the sampling procedure to the specification of the standard (see par. 7) can be guaranteed only when sampling is carried out by CATAS Technicians.

Sampling not accredited by ACCREDIA

*This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.*

Managing Director  
Dr. Andrea Giavon

The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer.

**TEST REPORT**

**149454 / 1**

Date received: 12/11/12  
Date of test: 20/11/12  
Date of issue: 28/11/12

D.K.Z. S.R.L.  
VIA DELL'ARTIGIANATO 8  
38037 PREDAZZO (TN)  
ITALIA  
Attn: sig. Walter Vuerich

Sample name: Serie boschi di fiamme, serie fiamme antica, serie luci di fiamme, serie mani di fiamme

**Formaldehyde release - EN 717-2:1994**

|                            |    |                              |
|----------------------------|----|------------------------------|
| Thickness                  | mm | 15,2                         |
| Moisture content           | %  | 7,4                          |
| Edges                      | -  | Sealed                       |
| Conditioning               | -  | Not required by the standard |
| Sampling                   | -  | Carried out by the customer  |
| Sample received dimensions | mm | Less than 500 x 500          |

Test results:

|                              |     |
|------------------------------|-----|
| mg HCHO/(m <sup>2</sup> · h) | 0,5 |
|------------------------------|-----|

|               |         |
|---------------|---------|
| Type of board | Parquet |
|---------------|---------|

*This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.*

Managing Director  
Dr. Andrea Glaven

The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer.