

FIOR DI RISERVA



As if it was wine ageing in prestigious wood barrels. This aged oak spread intense glares and bursts of toasted-like colour in a general sensation of balance and sobriety.

Technical specific

Wood	Oak
Thickness	15 mm
	Th.top layer 4 mm
Width	Multi-width*
Length	from 700 to 3000 mm
Selection	Variegated
Back	Spruce
Origin	European Union
Fire resistance class	Cfl-s1
Formaldehyde emission	E1 (<0,1ppm)
Conductivity	0,14 W/mK
Thermal resistance	0,10 K/W
Weight	9 Kg/mq
Humidity	10%+ / -2%
Hardness	23-42 N/mm ²

*Multi-width: from 3 to 5 mixed types of width, according to quality and availability

